



### 铭客AT1000是一种奥氏体钼合金不锈钢钢带,其特点是:

MINGKE AT1000 is an austenitic molybdenum alloyed stainless steel belt and it is characterized by:

• 静态强度适中 Fair static strength

- 中等耐磨性 Fair wear resistance
- 良好的疲劳强度 Good fatigue strength
- 优异的耐腐蚀性 Excellent corrosion resistance
- 很好的可修复性 Very good repairability
- 它是一种具有很高的可修复性的高度耐腐蚀钢带,使其非常适合化学工业和其他严重腐蚀 行业应用。

It is a highly corrosion resistant steel with very good repairability. This makes it good for processes in chemical industries and other severe corrosive applications.

### 化学成分(公称值)

### Chemical Composition (Nominal) %

碳c	锰Mn	磷P	硫 s	硅 Si	铬 Cr	镍 Ni	钼 Mo	氮 N	铁 Fe
≤0.08	≤2.00	≪0.05	≤0.03	≤1.00	16.00-18.00	10.00-15.00	2.00-3.00	≤0.10	-

## 静态强度

# 室温下的标准强度(公称数值)

Static Strength

Standard strength at room temperature (nominal values)

参 <u>量</u> Parameters	抗拉强度 Tensile strength		屈服强度 Yield strength		延伸率 Elongation	焊接系数 Weld factor	硬度 Hardness
	Мра	Ksi	Мра	Ksi	A5(%)	Rm/Rm	HV5
母材 Parent material	1000	145	780	113	10	*	320
焊接区域 Welding Area	700	102	500	73	6	0.70	*

# 供货范围

Scope of Supply

 长度 Length:可定制 customize available

 宽度 Width: 800/1000/1200/1540/2000/...mm

 厚度 Thickness: 0.5/0.8/1.0/1.2 mm

 提示:单幅钢带最宽宽度 2000mm,特殊规格可以定制。

 Tips: Max. width of a single belt is 2000mm, customized sizes via cutting is available.

\*本资料中数据具代表性但并不受到绝对保证。数据亦会因材料批次不同而改变。

\* The data in this sheet are typical values, but not guaranteed. The information is subject to changes in different batches of material.