



**MT1650 不锈钢钢带**  
**MT1650 Stainless Steel Belt**



铭客MT1650是一种基于铬镍铜的低碳沉淀硬化马氏体15-7PH不锈钢钢带。其特点是：

MINGKE MT1650 is a kind of low carbon chromium-nickel-copper precipitation hardening martensitic 15-7PH stainless steel belt. It's characterized by:

- 出色的机械性能 Excellent mechanical properties
- 良好的耐腐蚀性 Good corrosion resistance
- 优异的静态强度 Excellent static strength
- 极好的耐磨性 Very good wear resistance
- 优异的疲劳强度 Excellent fatigue strength
- 很好的可修复性 Very good repairability

### 化学成分(公称值)

*Chemical Composition (Nominal) %*

碳 C	硅 Si	锰 Mn	磷 P	硫 S	铬 Cr	镍 Ni	钛 Ti	铜 Cu	钼 Mo	氮 N	铁 Fe
0.04	1.59	0.48	0.02	0.001	14.02	7.01	0.34	0.69	0.84	0.008	-

### 静态强度

#### 室温下的标准强度(公称数值)

*Static Strength*

*Standard strength at room temperature (nominal values)*

参数 Parameters	抗拉强度 Tensile strength		屈服强度 Yield strength		延伸率 Elongation		焊接系数 Weld factor		硬度 Hardness					
	Mpa		Ksi		Mpa		Ksi		A5(%)		Rm/Rm		HV5	
母材 Parent Material	1600		232		1550		225		5		*		480	
焊接区域(未热处理) Welding area (not heat treated)	1150		167		1100		160		5		0.70		*	
焊接区域(热处理) Welding area (heat treated)	1300		188		1250		181		3		0.80		*	

### 供货范围

*Scope of Supply*

长度 Length: 可定制 customize available
宽度 Width: 1000 / 1200 / 1550 / ... mm
厚度 Thickness: 1.0 / 1.2 / 1.6 / 1.8 / 2.0 / 2.3 / 2.7 / 3.0 / 3.5 mm
提示: 单幅钢带最宽宽度 1550mm, 超过此宽度需要纵向拼接。特殊规格可以定制。 Tips: Max. width of a single belt is 1550mm, customized sizes via cutting or longitudinal welding are available.

\* 本资料中数据具代表性但并不受到绝对保证。数据亦会因材料批次不同而改变。

\* The data in this sheet are typical values, but not guaranteed. The information is subject to changes in different batches of material.